



QuickSeam Corner Flashing

1. Description

QuickSeam Corner Flashing is a self-curing round rubber piece with a diameter of 216mm, adaptable to irregular shapes and designed to flash system details (inside and outside corners, reinforcement patches...) in accordance with Firestone specifications. The FormFlash layer is factory laminated to QuickSeam Tape.

2. Preparation

The EPDM geomembrane surfaces must be prepared with QuickPrime Plus, using a QuickScrubber tool. Use of other products is not allowed. Restore the Corner Flashing to room temperature prior to use if exposed to temperatures below 15°C for prolonged periods.

3. Application

On cloudy days with ambient temperature below 15°C, the use of a heat gun is recommended to warm the QuickSeam Corner Flashing and ensure good formability.

On sunny days, pre-heating of the product is usually not necessary. On sunny days less than 20°C, place QuickSeam Corner Flashing (prior to application) with flashing side up to allow QuickSeam Corner Flashing to warm to ensure good formability. On sunny days greater than 20°C, place QuickSeam Corner Flashing (prior to application) with release paper side up to prevent QuickSeam Corner Flashing from gaining too much heat.

QuickSeam Corner Flashing is to be applied as per the Firestone specifications and details.

4. Coverage

In accordance with length of detail. Pieces must extend a minimum of 75mm beyond critical points.

5. Characteristics

The Firestone QuickSeam Corner Flashing is a rubber material with the following properties:

Technical	EPDM Flashing	QuickSeam Tape
• Base	EPDM	rubber polymers
• Color	black	black
• Solvents	none	none
• Solids(%)	100	100
• State	uncured	cured
• Thickness	1.6mm	0.6mm

6. Precautions

Take care when moving, transporting or handling to avoid sources of punctures and physical damage. Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from Firestone QuickSeam Corner Flashing. As long as product is not fully cured, QuickSeam Corner Flashing has limited chemical and root resistance.

Store in original unopened carton at temperatures between 15°C and 25°C. Keep the material out of direct sunlight until ready for application.

Shelf life is expected to be 12 months, when stored in above-mentioned conditions. Verify production date on each roll. Shelf life will be reduced if exposed to higher temperatures.